

## AF1701 Data Sheet S102-R85

### Silicone S102 – Red (FDA, Peroxide Cross Linked)

#### General

S102-R85 is a red Methyl Silicone Rubber, commonly referred to as Silicone. Silicone materials are often used in hot air and in applications where chemicals and foodstuff are in contact with the sealing material. Because of lower mechanical properties Silicone materials should not be used for dynamic applications. Silicone S102 – red is approved for the use of applications in contact with foodstuff.

#### Physical properties

Density	DIN 53479	g/cm <sup>3</sup>	1,54
Hardness at 20°	DIN 53505	Shore A	85 +/-5
Tensile strength	DIN 53504	N/mm <sup>2</sup>	7,4 +/-15%
Elongation at break	DIN 53504	%	120 +/-20%
Modulus 100%	DIN 53504	N/mm	-
Tear strength	DIN 53507B	N/mm	10
Compression set: 70h/RT	DIN 53517A	%	10,8 +/-25%
Compression set: 22h/70°C	DIN 53517A	%	10,6 +/-25%
Compression set: 22h/100°C	DIN 53517A	%	6,8 +/-25%
Compression set: 22h/175°C	DIN 53517A	%	20,4 +/-20%
Min. service temperature		°C	-55
Max. service temperature		°C	210
Short time max. service temp. in air		°C	270

#### Chemical resistance

Water up to 90°	R	Vegetable oils	R
Steam below 120°	R	Silicone oils	U
HFA, HFB, HFC fluids	R	Fuels	U
HFD-R, -S	R	Ozone, oxygen	R
Mineral oils	S	Air up to 200°C	R

Key to chemical resistance: R = Resistant S = Suitable U = Unsuitable

#### Main application

Static and dynamic seals (standard and special), wipers, O-rings, flange seals, rotary seals, rubber energizers (preload elements). Due to its low mechanical properties it should be used for static applications only. Chemical and food industry.

#### Analysis and evaluation

The mentioned properties are only valid for test pieces of the corresponding ISO, DIN and ASTM standards. They cannot be directly related to seals, gaskets and other sealing products and should be used only as a general guide.

Issued July 2013 AFT Fluorotec Technical Department.

All information is based on typical test results performed under specific conditions and limited sample size. This does not represent a legally binding guarantee of certain properties or the suitability for specific applications.

#### AFT Fluorotec

Solutions and components in Fluoropolymer Plastics

**Phone:** +44 (0) 1992 515880  
**Fax:** +44 (0) 1992 554490  
**Email:** info@fluorotec.com  
**Website:** www.fluorotec.com

Unit 2, Pages Old Mill  
Tamworth Road  
Hertford  
Herts. SG13 7DG