

AF106 Molybdenum Disulphide and Glass Fibre Filled PTFE

Glass fibre is the most commonly used filler in PTFE. It gives much improved compression and wear properties. The addition of Molybdenum Disulphide greatly improves the materials self lubrication properties particularly in dynamic sealing applications.

Typical Physical properties

Property	Test Method	Value
Specific Gravity	ASTM D 4894	2.24 – 2.28 g/cm ³
Tensile Strength	ASTM D 4894	19 – 23.5 MPa (2800-3400 PSI)
Elongation	ASTM D 4894	260 - 500%
Shore D Hardness	BS EN 13000-2	60
Coefficient of Friction	BS EN 13000-2	0.06

Issued March 2015 AFT Fluorotec Technical Department

All information is based on typical test results performed under specific conditions and limited sample size. This does not represent a legally binding guarantee of certain properties or the suitability for specific applications. All information is provided in good faith at time of print.

AFT Fluorotec

Solutions and components in Fluoropolymer Plastics

Phone: +44 (0) 1992 515880
Fax: +44 (0) 1992 554490
Email: info@fluorotec.com
Website: www.fluorotec.com

Hertford Town Mill
 Tamworth Road
 Hertford
 Herts. SG13 7DJ