

## AF1301 Data Sheet HN112-B85

### H-NBR HN112 – Black (Peroxide Cross Linked)

#### General

HN112-B85 is a black hydrogenated acrylonitrile-butadiene-rubber commonly referred to as H-NBR. Good physical characteristics and chemical resistance to the most common hydraulic fluids makes it an excellent sealing material. H-NBR materials are often used in vegetable and animal oils as well as in high addivated oils, sour oils/gases (H<sub>2</sub>S) and crude oils.

#### Physical Properties

Density:	DIN 53479	g/cm <sup>3</sup>	1,23
Hardness at 20°:	DIN 53505	Shore A	85 +/-5
Tensile strength:	DIN 53504	N/mm <sup>2</sup>	21,7 +/-15%
Elongation at break:	DIN 53504	%	215 +/-20%
Modulus 100%:	DIN 53504	N/mm	–
Tear strength	DIN 53507B	N/mm	6,6
Compression set: 70h/RT	DIN 53517A	%	–
Compression set: 22h/70°C	DIN 53517A	%	20,2 +/-20%
Compression set: 22h/100°C	DIN 53517A	%	22,3 +/-20%
Min. service temperature:		°C	-25
Max. service temperature:		°C	150

#### Chemical Resistance

Water up to 90°	R	Vegetable Oils	R
Sea Water	R	Silicone Oils	R
Steam	U	Biodegradable Oils	R
HFA, HFB Fluids	R	Fuels	S
HFC Fluids	S	Ozone, Oxygen (cold)	R
HFD Fluids	U	Air up to 100°	R
Mineral Oils	R	Air up to 150°	U

Key to chemical resistance: R = resistant S = suitable U = unsuitable

#### Main application

Static and dynamic seals (standard and special), wipers, O-rings, flange seals, rotary seals, rubber energizers (preload elements). General application in petroleum fluids, water, greases, mineral oils, oil and gas industry.

#### Analysis and Evaluation

The mentioned properties are only valid for test pieces of the corresponding ISO, DIN and ASTM standards. They cannot be directly related to seals, gaskets and other sealing products and should be used only as a general guide.

Issued February 2021 AFT Fluorotec Technical Department

All information is based on typical test results performed under specific conditions and limited sample size. This does not represent a legally binding guarantee of certain properties or the suitability for specific applications. All information is provided in good faith at time of print.

#### AFT Fluorotec

Solutions and components in Fluoropolymer Plastics

**Phone:** +44 (0) 1992 515880

**Email:** info@fluorotec.com

**Website:** www.fluorotec.com