

AF1003 Data Sheet U203-B95

Polyurethane U203 – Blue (FDA)

General

U203-B95 is a hydrolysis resistant PU (H-PU) composed of prepolymers based on polyadepthate glycols and diphenylmethane diisocyanate (MDI). The hardness is adjusted at 93 +/-2 Shore A. The product is recommended for a continuous use in 70 – 90°C hot water and a max. service temperature of 100°C. The system passed all official FDA tests by the Akron Polymer Laboratory Inc. – Ohio, U.S.A.

Physical Properties

Density:	DIN 53479	g/cm ³	1,10
Hardness at 20°:	DIN 53505	Shore A	93 +/-2
100% modulus:	DIN 53504	N/mm ²	> 10
300% modulus:	DIN 53504	N/mm	> 16
Tensile strength:	DIN 53504	N/mm ²	40
Elongation at break:	DIN 53504	%	460
Tear strength:	DIN 53515	kN/m	135
Rebound resilience:	DIN 53512	%	38
Abrasion loss:	DIN 53516	mm ³	< 35
Compression set:*	DIN 53517	%	31
Hardness at -5°:	DIN 53505	Shore A	96
Hardness at +80°C:	DIN 53505	Shore A	93
Min. service temperature:		°C	-30
Max. service temperature:		°C	105

*Compression set: 25% deflection, 22 hours at 70°C

Chemical Resistance

Water, sea water	R	HFA, HFB fluids	R
Demineralised water	R	HFC fluids	S
Steam	U	HFD fluids	U
Mineral/vegetable oils	R	Fuels, grease	S
Peanut oil	R	Alcohol, white spirit	S
Beer	R		

Key to chemical resistance: R = resistant S = suitable U = unsuitable

FDA certification (n-Hexane and water extraction test)

The following polyurethane elastomer system 'U203-B95 polyurethane blue' is approved for the use in applications that will come in contact with dry, and/or aqueous and/or fatty foodstuff. Tests have been performed in accordance with the US code for federal reg.

177-2600. Both n-Hexane and water extractables tests acc. to FDA CFR 177-2600 were performed by Akron Polymer Laboratory, Ohio, U.S.A. The tests determine if elastomer formulations can be used with dry, and/or wet, and/or oily foodstuffs. The results clearly show that the formulation passed the FDA requirements.

Analysis and Evaluation

The mentioned properties are fundamental values for polyurethane products. Values mentioned above are corresponding to the European ASTM and DIN standards and have been tested on test samples in the laboratory. All immersion tests in the laboratory are made on test samples under normal conditions for sealing products.

Issued February 2021 AFT Fluorotec Technical Department

All information is based on typical test results performed under specific conditions and limited sample size. This does not represent a legally binding guarantee of certain properties or the suitability for specific applications. All information is provided in good faith at time of print.

AFT Fluorotec

Solutions and components in Fluoropolymer Plastics

Phone: +44 (0) 1992 515880

Email: info@fluorotec.com

Website: www.fluorotec.com